

Chemical Composition of Composite bond LC

Formulation

	w/w
Methyl Methacrylate	10.13%
Butylated Hydroxy Toluene	0.15%
Bisphenol - A- Glycidol Methacrylate	40.38%
Urethane dimethacrylate	40.38%
Camphoroquinone	0.65%
Dimethyl Aminio Ethyl Methacrylate	0.52%
Ethenol	7.60%
Tetra Hydrofurfuryl Acrylate	4.96%

Product code; 2100 - 1