

## Chemical Composition of Gem Bond

### Catalyst

		w/w
Urethane dimethacrylate	60.70%	
Isopropanol	38.00%	
Natural Oil	0.60%	
Inhibitor	Trace	
Catalyst	0.10%	
Stabiliser	0.30%	
2- (dimethylamino) Ethyl methacrylate	0.30%	

### Base

Bisphenol A Diglycyl methacrylate	49.40%
Tetrahydrofurfuryl -2-methacrylate	49.10%
Natural oil	0.60%
Initiator	0.10%
Stabiliser	0.30%
2-(dimethylamino) Ethyl methacrylate	0.50%

Product code; 2100