

Chemical Composition of Composite Tints

Formulation

	w/w
Bisphenoil A diglycidyl methacrylate	17.1%
Ethylene glycol dimethacrylate	8.6%
Alumino silico phospho fluoro glass	62.2%
Silica	1.6%
Inhibitor	Less than 0.2%
Silane coupling agent	Trace
Approved pigments	10.0%